

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (Currently Amended) A decorative laminate comprising:
a decorative layer comprising a thermosetting resin impregnated cellulosic material; and
a core layer below said decorative layer comprising polyethylene terephthalate glycol.
2. (Original) The decorative laminate of claim 1, wherein said decorative laminate is a high pressure decorative laminate.
3. (Original) The decorative laminate of claim 1, wherein said decorative laminate is a low pressure decorative laminate.
4. (Original) The decorative laminate of claim 1, wherein said decorative laminate is a continuous laminate.
5. (Previously Amended) The decorative laminate of claim 1, wherein said polyethylene terephthalate glycol is at least one sheet of polyethylene terephthalate glycol.
6. (Previously Amended) The decorative laminate of claim 1, wherein said core layer further comprises at least one layer of a woven or non-woven sheet formed from a material selected from the group consisting of glass, carbon and polymeric fiber.
7. (Previously Amended) The decorative laminate of claim 6, wherein said at least one layer is sandwiched in between two polyethylene terephthalate glycol sheets.

8. (Original) The decorative laminate of claim 1, wherein said decorative laminate further comprises an overlay layer on top of said decorative layer.
9. (Original) The decorative laminate of claim 8, wherein said overlay layer includes abrasive particles.
10. (Original) The decorative laminate of claim 9, wherein said abrasive particles comprise alumina.
11. (Original) The decorative laminate of claim 8, wherein said overlay layer is impregnated with a melamine formaldehyde resin.
12. (Original) The decorative laminate of claim 1, wherein said decorative layer is impregnated with a melamine formaldehyde resin.
13. (Original) The decorative laminate of claim 1, wherein said decorative layer includes a printed pattern.
14. (Currently Amended) A decorative laminate comprising:
a wear resistant layer comprising a thermosetting resin impregnated cellulosic material;
a decorative layer comprising a thermosetting resin impregnated cellulosic material; and
a core layer below said decorative layer comprising at least one sheet of polyethylene terephthalate glycol.
15. (Original) The decorative laminate of claim 14, wherein said decorative laminate is a high pressure decorative laminate.
16. (Original) The decorative laminate of claim 14, wherein said decorative laminate is a low pressure decorative laminate.

17. (Original) The decorative laminate of claim 14, wherein said decorative laminate is a continuous laminate.

18. (Original) The decorative laminate of claim 14, wherein said wear resistant layer is an overlay layer on top of said decorative layer, said overlay layer including abrasive particles.

19. (Original) The decorative laminate of claim 18, wherein said abrasive particles comprise alumina.

20. (Withdrawn) A decorative laminate assembly comprising, ~~in order in the following superimposed relationship:~~

(a) a decorative laminate top layer assembly comprising, ~~in order in a superimposed relationship:~~

(i) a decorative layer comprising a thermosetting resin impregnated cellulosic material,

(ii) a core layer below said decorative layer comprising PETG polyethylene terephthalate glycol; and

(b) a substrate attached to said decorative laminate top layer assembly.

21. (Withdrawn) The decorative laminate of claim 20, wherein said decorative laminate is a high pressure decorative laminate.

22. (Withdrawn) The decorative laminate of claim 20, wherein said decorative laminate is a low pressure decorative laminate.

23. (Withdrawn) The decorative laminate of claim 20, wherein said decorative laminate is continuous laminate.

24. (Withdrawn) The decorative laminate of claim 20, wherein said ~~PETG~~ polyethylene terephthalate glycol is at least one sheet of ~~PETG~~ polyethylene terephthalate glycol.

25. (Withdrawn) The decorative laminate of claim 20, wherein said core layer further comprises at least one layer of a woven or non-woven sheet formed from a material selected from the group consisting of glass, carbon or polymeric fiber.

26. (Withdrawn) The decorative laminate of claim 25, wherein said at least one layer is sandwiched in between two ~~PETG~~ polyethylene terephthalate glycol sheets.

27. (Withdrawn) The decorative laminate of claim 20, wherein said decorative laminate further comprises an overlay layer on top of said decorative layer.

28. (Withdrawn) The decorative laminate of claim 27, wherein said overlay layer includes abrasive particles.

29. (Withdrawn) The decorative laminate assembly of claim 20, wherein said substrate is water resistant.

30. (Withdrawn) The decorative laminate assembly of claim 29, wherein said water resistant substrate comprises polyvinyl chloride.

31. (Withdrawn) The decorative laminate assembly of claim 29, wherein said water resistant substrate comprises fiber reinforced cement board.

32. (Withdrawn) The decorative laminate assembly of claim 20, wherein said substrate is attached to said top layer assembly with a water resistant adhesive.

33. (Withdrawn) A decorative laminate assembly comprising, ~~in order in the following superimposed relationship:~~

(a) a high pressure decorative laminate top layer assembly comprising, ~~in order in a superimposed relationship:~~

(i) a wear resistant layer;

(ii) a decorative layer comprising a thermosetting resin impregnated cellulosic material; and

(iii) a core layer below said decorative layer comprising PETG polyethylene terephthalate glycol;

(b) a water resistant adhesive layer;

(c) a water resistant substrate, wherein said water resistant adhesive layer bonds together said top layer assembly to said water resistant substrate.

34. (Withdrawn) The decorative laminate of claim 33, wherein said decorative laminate is a high pressure decorative laminate.

35. (Withdrawn) The decorative laminate of claim 33, wherein said decorative laminate is a low pressure decorative laminate.

36. (Withdrawn) The decorative laminate of claim 33, wherein said decorative laminate is continuous laminate.

37. (Withdrawn) The decorative laminate of claim 33, wherein said ~~PETG~~ polyethylene terephthalate glycol is at least one sheet of ~~PETG~~ polyethylene terephthalate glycol.

38. (Withdrawn) The decorative laminate of claim 33, wherein said wear resistant layer is an overlay layer on top of said decorative layer, said overlay layer including abrasive particles.

39. (Withdrawn) The decorative laminate assembly of claim 33, wherein said water resistant substrate comprises polyvinyl chloride.

40. (Withdrawn) The decorative laminate assembly of claim 33, wherein said water resistant substrate comprises fiber reinforced cement board.

41. (Withdrawn) The decorative laminate of claim 33, wherein said core layer further comprises at least one layer of a woven or non-woven sheet formed from a material selected from the group consisting of glass, carbon or polymeric fiber.
42. (Withdrawn) The decorative laminate assembly of claim 41, wherein said at least one layer is sandwiched in between two ~~PETG~~-polyethylene terephthalate glycol sheets.
43. (Withdrawn) A method for producing a decorative laminate comprising:
- (a) assembling, ~~in order in the following superimposed relationship~~, a wear resistant layer, a decorative layer comprising a thermosetting resin impregnated cellulosic material and a core layer below said decorative layer, said core layer comprising ~~PETG~~ polyethylene terephthalate glycol; and
 - (b) subjecting said assembly to heat and pressure, thereby laminating said assembly.
44. (Withdrawn) The method of claim 43, wherein said wear resistant layer is an overlay layer, said overlay layer including abrasive particles.
45. (Withdrawn) The method of claim 43, wherein said ~~PETG~~-polyethylene terephthalate glycol is 0.020 inches thick.
46. (Withdrawn) The method of claim 43, wherein said pressure is between 1000 and 1200 psig.
47. (Withdrawn) The method of claim 46, wherein said temperature is between 125°C and 127°C.
48. (Withdrawn) The method of claim 47, wherein said heat and pressure is maintained for 25-30 minutes.

49. (Withdrawn) The method of claim 43, further comprising bonding said overlay layer, decorative layer, and core layer to a water resistant substrate after said subjecting to heat and pressure laminating step.
50. (Withdrawn) The method of claim 49, wherein said water resistant substrate comprises PVC.
51. (Withdrawn) The method of claim 49, wherein said water resistant substrate comprises fiber reinforced cement board.
52. (Withdrawn) The method of claim 49, wherein said ~~PETG~~polyethylene terephthalate glycol comprises at least one sheet of ~~PETG~~polyethylene terephthalate glycol.
53. (Previously Presented) The decorative laminate of claim 1, wherein said cellulosic material is impregnated prior to lamination.
54. (Previously Presented) The decorative laminate of claim 1, wherein said cellulosic material is impregnated during the lamination process.
55. (Previously Presented) The decorative laminate of claim 14, wherein said cellulosic material of at least said decorative layer is impregnated prior to lamination.
56. (Previously Presented) The decorative laminate of claim 14, wherein said cellulosic material of at least said decorative layer is impregnated during the lamination process.